

# Facing Brick Technical Information Sheet

BLOCKLEYS

## Roseberry

Configuration:	Vertically Perforated Clay Facing Brick		
Size:	215 x 102.5 x 73 mm		
Dimensional Tolerance:	T2	Dimensional Range:	R2
Density - Net:	2290	kg/m <sup>3</sup>	Density - Tolerance: D1
Density - Gross:	1640	kg/m <sup>3</sup>	
Compressive Strength:	50	N/mm <sup>2</sup>	Compressive Strength Category: II
Water Absorption:	12.0	%	
Soluble Salts Category:	S2		
Durability:	F2		
Thermal Conductivity P=50:	0.72	W/m.K	
Thermal Conductivity P=90:	0.79	W/m.K	
Water Vapour Permeability Coefficient:	50/100		
Dangerous Substances:	N/A		

Bricks are manufactured and supplied to relevant clauses of EN 771-1  
Declarations of Performance, Environmental and other policies can be found on the company website:  
[www.mbhplc.co.uk](http://www.mbhplc.co.uk)

Further information is available through our sales department.  
Tel: 0844 9310022 email: [sales@mbhplc.co.uk](mailto:sales@mbhplc.co.uk)