## PRODUCT SPECIFICATION

## Information correct as at 04 November 2022

Description

**Product Name** Shireoak Russet

Product Code A0085A

Quality Best **CLAY FACING BRICK** 

Manufacturing Unit Aldridge Factory Type Wirecut Extruded

Configuration **Vertically Perforated** 

Voids 23-28

**Specification** (In accordance with BS EN771-1:2011/A1:2015)

Masonry Unit Group **HD units Group 2 Structural** 

Category BS EN771-1:2011/A1:2015 Cat I

Dimensions 215x102x65 mm

+/-L4W3H2 Tolerance - Mean T2 **L9W6H5** Tolerance - Range R1

Bed Surface Mean >=35.0 N / mm<sup>2</sup>

Compressive Strength

**Additional Data** 

1480 kg/m<sup>3</sup> **Gross Density** 2060 kg/m<sup>3</sup> **Nett Density** 

**Density Tolerance D1** 

Severe Exposure Durability F2

Active Soluble Salts S2

<=12 % by weight Water Absorption

laitial rights of water n Rate 1.1 kg/m/min

Fire Reaction Euroclass A1

Water Vapour Diffusion Coefficient 50/100 mu (Water Vapour Permeability) Bond Strength - Fixed Value 0.15 N/mm

Stated as Initial Shear Strength

**Thermal Properties** (Tabulated - CIBSE Guide A 1999/BSEN 1745)

Thermal Conductivity 'K' W/mK 1.01

(at 5% moisture content - exposed)

m<sup>2</sup>K/W Thermal Resistance 'R' 0.1

(at 5% moisture content - exposed)

**Handling Information** 

2.1 kg Dry Weight per brick

186.0 kg/m<sup>2</sup> Average weight of brickwork

(1/2 brick wall including mortar joints)

Coverage Approximately 60.0 bricks per m

Quantity per pack 316

Pack Size (WxDxH) 715x860x780 mm Weight per pack (dry) 664 kg approximately

**Application** 

To be used in accordance with BS EN1996, PD6697 and Suitability

our own recommendations

Mortar Joint Profile From a durability point of view, this product is suitable for

all common joint profiles

Movement joints should be incorporated in accordance with Movement Joints

BS EN1996. PD6697 and our own recommendations

**Special Shapes** Special shapes are only available by the cut

and bonding method

**Quality Assurance** 

Frost Resistance This product is guaranteed for 60 years in buildings or 20

years in boundary walls. Excludes paving, steps & ramps. All applications should be designed and constructed in accordance with the

guidance contained within BS EN1996, PD6697 and with our own recommendations.

Failure to comply will invalidate all warranties implied.

Workmanship

Mixing from a minimum of three packs on site will ensure a balanced Colour

blend of all the colours formed in the manufacturing process

Test results derived under BS EN 771-1 must be used in conjuction with BS EN1996, PD6697