




## **Product Technical Information Sheet** Wienerberger Code 24177010 **Production Plant** Denton Manufacture Extruded/Wirecut Perforated Configuration Red Multi Colour Sanded Appearance 215 x 102.5 x 73 Work Size (L x W x H) **Pack Quantity** 340 No. Individual Dry Brick Weight (kg) 2.3



## **Technical Properties to BS EN 771-1**

Size Tolerance (Mean/Range)	T2/R1
Gross Dry Density (kg/m³/Tolerance)	1480 (D1)
Compressive Strength (N/mm²)	≥40
Thermal Conductivity (W/(m·K))	P=90% 0.69
Durability Designation	F2
Water Absorption (%)	≤12
Initial Rate of Water Absorption (kg/(m²·min))	Min. 1.0 Max. 2.2
Active Soluble Salts	S2
Reaction to Fire	Class A1

## Issue Date: 07/09/2020

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.





1000+ products to choose from



Expert help and advice



Comprehensive Design Services



**Technical Support** 

